

# **Confidential Report**

Our Ref: 23/61405i/09/23







Client:

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 26 September 2023

Our Ref: 23/61405i/09/23

Your Ref: --

Page: 1 of 6

Westbury Textiles Australia

19 Abrams Street Balcatta WA 6021 Perth Australia

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 22 September 2023

Date Test Started: 26 September 2023

Description of Sample: One sample of fabric, which was referenced by the client as;


Villandry FR - Antique Slate, stated to be 100% Polyester FR

Work Requested: We were asked to test the received sample to the following standard:

BS EN 1021:Parts 1 & 2:2014 - Ignitability of Upholstered Furniture

- subcontracted test, UKAS accredited
- \* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 26 September 2023

Our Ref: 23/61405i/09/23 Your Ref: --

Page: 2 of 6

Client: Westbury Textiles Australia

## FIRE TEST ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

#### **Pre-Treatment**

The material received no pre-treatment as the fabric is stated to not have an FR treatment.

# Conditioning

The materials for testing to Source 0 and 1 were conditioned for a minimum of 24 hours and tested in the environments specified in Clause 7 of BS EN 1021-1 & 2:2014.

The sample was tested in a room of volume 25m<sup>3</sup> and 21°C.

# Procedure

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m<sup>3</sup>.

Tests were made using ignition source 0.

# Requirements

The specimens shall not:-

# **Smouldering Criteria**

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) on final examination, show evidence of progressive smouldering.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

26 September 2023 Date:

Our Ref: 23/61405i/09/23 Your Ref:

> Page: 3 of 6

**Client: Westbury Textiles Australia** 

# Requirements (continued)

# Flaming Criteria

a) show evidence of flaming initiated by a smouldering source.

#### Results

Smouldering criteria	Specimen No.		
	1	2	<b>3</b> ¹
Unsafe escalating combustion	No	No	
Testing assembly consumed	No	No	
Smoulders to extremities/full thickness	No	No	
Smoulders more than 1 hour	No	No	
In final examination, presence of progressive	No	No	
smouldering			

Flaming criteria	1	2	3 <sup>1</sup>
Occurrence of flames	No	No	
Specimen Result Ignition (I) / Non Ignition (NI)	NI	NI	

Any "Yes" in smouldering or flaming criteria means Ignition

#### Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

# **Comments**

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.





1066



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 26 September 2023

Our Ref: 23/61405i/09/23 Your Ref:

Page: 4 of 6

Client: **Westbury Textiles Australia** 

# FIRE TESTS ACCORDING TO BS EN 1021-2:2014

Assessment of the ignitability of upholstered furniture. Part 2. Ignition Source 1: Match flame equivalent.

#### **Pre-Treatment**

The material received no pre-treatment as the fabric is stated to not have an FR treatment.

# Conditioning

The sample was conditioned for at least 24 hours at a temperature of  $23\pm2^{\circ}$ C and relative humidity of  $50\pm5\%$ .

The sample was tested in a room of volume 25m<sup>3</sup> and 21°C.

#### **Procedure**

The test was carried out in accordance with BS EN 1021-2:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m<sup>3</sup>.

Tests were made using ignition source 1.

# Requirements

The specimens shall not:-

# **Smouldering Criteria**

- display escalating combustion requiring active extinction. a)
- b) smoulders until it is essentially consumed within the test duration.
- c) smoulder to the extremities of the specimen, or through the full thickness, within the duration of the test.
- smoulder for more than one hour. d)
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

26 September 2023 Date:

Our Ref: 23/61405i/09/23 Your Ref:

> Page: 5 of 6

**Client: Westbury Textiles Australia** 

# **Requirements (Continued)**

# Flaming Criteria

- a) display escalating combustion requiring active extinction.
- b) burns until it is essentially consumed within the test duration.
- c) burns to the extremities of the specimen, or through the full thickness, within the duration of the test.
- exhibit any flaming for more than 120 seconds after removal of the burner tube. d)

#### Results

		Specimen No.	
Smouldering criteria	1	2	3 <sup>1</sup>
Unsafe escalating combustion	No	No	
Testing assembly consumed	No	No	
Smoulders to extremities/full thickness	No	No	
Smoulders more than 1 hour	No	No	
In final examination, presence of	No	No	
progressive smouldering			

Flaming criteria	1	2	31
Unsafe escalating combustion	No	No	
Testing assembly consumed	No	No	
Flames to extremities/full thickness	No	No	
Flames longer than 120 seconds	No	No	
Specimen Result Ignition (I) / Non Ignition (NI)	NI	NI	

#### Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

26 September 2023 Date:

Our Ref: 23/61405i/09/23

Your Ref:

Page: 6 of 6

**Client: Westbury Textiles Australia** 

# **Comments**

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-2.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

# **Uncertainty Budget**

The overall uncertainty budget for both BS EN 1021: Part 1 and 2:2014 is as follows:-

Timings: ±2 seconds. Measurements: ±2mm.

Reported by:..... ...... R Greasley, Laboratory Technician

Countersigned by:..... ..... B Bland, Technical Customer Service Officer

Enquiries concerning this report should be addressed to Customer Services.





1066